

COMPLETE LISTING OF CLAIMS
IN ASCENDING ORDER WITH STATUS INDICATOR

Claims 1-5 (Cancelled)

Claim 6. (Currently amended) A molded article comprises a transparent plastic film having a hard-coating layer on one surface of a plastic base film, wherein, with x (μm) representing a thickness of said base film, and y (%) representing an elongation percentage at the time when said plastic film having the hard-coating layer is pulled under a condition at 22°C with one side fixed and at a pulling speed of 20 mm/min, no crack is generated in the hard-coating layer in a region satisfying a relationship:

$$y < 5.7 \text{ if } x \leq 100,$$

$$y < -0.018x + 7.5 \text{ if } 100 \leq x \leq 150,$$

$$y < -0.008x + 6.0 \text{ if } 150 \leq x \leq 200,$$

$$y < -0.005x + 5.4 \text{ if } 200 \leq x \leq 300,$$

$$y < -0.003x + 4.8 \text{ if } 300 \leq x \leq 400, \text{ and}$$

$$y < -0.002x + 4.4 \text{ if } 400 \leq x \leq 500,$$

when a tensile test is carried out under said condition,

wherein said plastic base film has a thickness of 500 μm or less, and said molded article is obtained by having the transparent plastic film ~~is used for obtaining a molded article having~~ the hard-coating layer given thereto by setting the transparent plastic film having the hard-coating layer on one surface of the plastic base film so that the hard-coating layer faces towards one mold surface in a mold for injection molding, clamping the plastic film so that a cavity is formed between a base surface of said film and the other mold surface, thereafter injecting a molten resin into said cavity and cooling the resin to mold a molded article body, and simultaneously to laminate and integrate said plastic film on a surface of the molded article body, in producing the plastic molded article by injection molding.

Claim 7. (Currently amended) A plate-shaped molded article comprises a transparent plastic film having a hard-coating layer on one surface of a plastic base film, wherein, with x

(μm) representing a thickness of said base film, and y (%) representing an elongation percentage at the time when said plastic film having the hard-coating layer is pulled under a condition at 22°C with one side fixed and at a pulling speed of 20 mm/min , no crack is generated in the hard-coating layer in a region satisfying a relationship:

$$y < 5.7 \text{ if } x \leq 100,$$

$$y < -0.018x + 7.5 \text{ if } 100 \leq x \leq 150,$$

$$y < -0.008x + 6.0 \text{ if } 150 \leq x \leq 200,$$

$$y < -0.005x + 5.4 \text{ if } 200 \leq x \leq 300,$$

$$y < -0.003x + 4.8 \text{ of } 300 \leq x \leq 400, \text{ and}$$

$$y < -0.002x + 4.4 \text{ if } 400 \leq x \leq 500,$$

when a tensile test is carried out under said condition,

wherein said plastic base film has a thickness of $500\text{ }\mu\text{m}$ or less, and said plate-shaped molded article is obtained by having the transparent plastic film ~~is used for obtaining a plate-shaped molded article~~ having the hard-coating layers given thereto on both surfaces by setting two sheets of the transparent plastic films having the hard-coating layer on one surface of the plastic base film so that the hard-coating layers respectively face towards one mold surface and the other mold surface in a mold for injection molding, clamping the plastic film so that a cavity is formed between base surfaces of said two sheets of the films, thereafter injecting a molten resin into said cavity and cooling the resin to mold a molded article body, and simultaneously to laminate and integrate said plastic films on both surfaces of the molded article body, in producing the plastic plate-shaped molded article by injection molding.